


Papir za neskončne obrazce  
 Papier für Endlosvordruck  
 Paper for continuous stationery usage



- |   |   |  |
|---|---|--|
| <ul style="list-style-type: none"> <li>· Primeren za laserske tiskalnike</li> <li>· Dobre mehanske lastnosti</li> <li>· Dobra dimenzionalna stabilnost</li> <li>· Primerna togost</li> <li>· Nizka abrazivnost (perforacija)</li> </ul> | <ul style="list-style-type: none"> <li>· Geeignet für Laserdrucker</li> <li>· Gute mechanische Eigenschaften</li> <li>· Gute Formbeständigkeit</li> <li>· Richtige Steifigkeit</li> <li>· Niedrigerer Abriebgrad (Durchlochen)</li> </ul> | <ul style="list-style-type: none"> <li>· Suitable for laser printers</li> <li>· Good mechanical properties</li> <li>· High dimensional stability</li> <li>· Adequate rigidity</li> <li>· Low abrasiveness (perforation)</li> </ul> |
|---|---|--|

STRUKTURA PAPIRJA | PAPIERSTRUKTUR | PAPER STRUCTURE



SPEEDFLOW TECHNOLOGY



**SPECIFIKACIJA PAPIRJA**  
**PAPIER SPEZIFIKATION**  
**PAPER SPECIFICATION**  
**AOP LASER 08.2000**

Goričane Tovarna papirja Medvode d.d.  
 Ladja 10, 1215 Medvode, Slovenija  
 Tel.: +386 1 58 23 400  
 Fax.: +386 1 36 13 319, 36 12 804  
 http://www.goricane.si  
 e-mail: goricane@goricane.si

**SORA AOP L**

PARAMETER	STANDARD NORM	ENOTA EINHEIT UNIT	SPECIFIKACIJA SPEZIFIKATION SPECIFICATION	TOLERANCA TOLERANZ TOLERANCE
Gramatura Flachengewicht Grammage	DIN EN ISO 536	g/m <sup>2</sup>	60,70,80,90, 100,110	± 2
Spec. volumen Spez. Volumen Spec. volume	DIN 53105	cm <sup>3</sup> /g	1,30	± 0,05
Gladkost Bendtsen Glatte Bendtsen Smoot. Bendtsen	ISO 8791-2	ml/min	200	± 50
Absolutna vlaga Abs. Feuchtigkeit Abs. humidity	DIN EN 20287	%	4.8	±0.5
ISO Belina ISO Weissgrad ISO Brightness R 457 nm (UV radiation included)	TAPPI 452	%	98	± 1
Opaciteta Opazität Opacity	ISO 2471	%	80,82,86,90, 93,95	min

Predstavnik vodstva: Marjan Kocjančič  
 Managementvertreter:  
 Management representative:

Spezifikacija ist nur für Information. Nach Einzelheiten fragen Sie beim Hersteller.  
 Specification is informative. For details contact the producer.