

Specifikacija papirja / Papierspezifikation / Paper Specification

TS – 15. 9. 2010

Parameter	Vrsta papirja	37	40	45	50	55	60	Toleranca Toleranz Tolerance
	Norm Standard							
Gramatura Flächengewicht Grammage [g/m ²]	ISO 536	37	40	45	50	55	60	± 2
Spec. volumen Spez. Volumen Spec. volume [cm ³ /g]	DIN 53105	1,25	1,25	1,25	1,25	1,25	1,25	± 0,05
Gladkost Bendtsen Glätte Bendtsen Smoot.Bendtsen [ml/min]	ISO 8791-2	150	150	150	150	150	150	± 50
Belina Weissgrad Brightness R 457nm (UV radiation included) [%]	ISO 2470 (D65/10°)	100	100	100	100	100	100	± 2
Opaciteta Opazität Opacity [%]	ISO 2471	73	76	79	82	84	86	± 2

Navedeni parametri so okvirni in se lahko spremenijo brez predhodne najave.

Die obigen genannten Parameter gelten als Richtwerte und können ohne vorherige Ankündigung geändert werden.

Given values can be used as guide values only and can be changed without prior notice.



SORA **medico**

