




Papir za ofsetni tisk
 Offsetdruckpapier
 Offset printing paper



- | | | |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <ul style="list-style-type: none"> · Naraven nepremazan papir · Primeren za ofset tisk · Dobre tiskarske lastnosti · Primeren za tisk knjig in brušur | <ul style="list-style-type: none"> · Naturpapier · Geeignet für Offsetdruck · Gute Druckeigenschaften · Geeignet für Bücher und Broschüren | <ul style="list-style-type: none"> · Natural uncoated paper · Suitable for offset printing · Good printing properties · Suitable for books and brochures |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

STRUKTURA PAPIRJA | PAPIERSTRUKTUR | PAPER STRUCTURE



SPEEDFLOW TECHNOLOGY



SPECIFIKACIJA PAPIRJA
PAPIER SPEZIFIKATION
PAPER SPECIFICATIONTS
PRESS 08.2000

Goričane Tovarna papirja Medvode d.d.
 Ladja 10, 1215 Medvode, Slovenija
 Tel.: +386 1 58 23 400
 Fax.: +386 1 36 13 319, 36 12 804
 http://www.goricane.si
 e-mail: goricane@goricane.si

SORA PRESS

PARAMETER	STANDARD NORM	ENOTA EINHEIT UNIT	SPECIFIKACIJA SPEZIFIKATION SPECIFICATION	TOLERANCA TOLERANZ TOLERANCE
Gramatura Flachengewicht Grammage	DIN EN ISO 536	g/m ²	60,70,80,90, 100,115	± 2
Spec. volumen Spez. Volumen Spec. volume	DIN 53105	cm ³ /g	1,25	± 0,05
Gladkost Bendtsen Glatte Bendtsen Smoot. Bendtsen	ISO 8791-2	ml/min	200	± 50
Relativna vlaga Rel. Feuchtigkeit Rel. humidity	DIN 19306	%	50	± 5
ISO Belina ISO Weissgrad ISO Brightness R 457 nm (UV radiation included)	TAPPI 452	%	96	± 1
Opaciteta Opazität Opacity	ISO 2471	%	81,85,88,90, 92,94	min

Predstavnik vodstva: Marjan Kocjančič
 Managementvertreter:
 Management representative:

Spezifikacija ist nur für Information. Nach Einzelheiten fragen Sie beim Hersteller.
 Specification is informative. For details contact the producer.